

製品一覧

Polymer	Polymer Type	Brookfield Viscosity cps (@190°C)	Needle Pen (dmm)	R&B Softing Point (°C)	Grass Transition (°C)	Open Time (sec)	Tensile Strength (Mpa)
RT2115A	Homopolymer	1,500	10	155	—	—	—
RT2180A	Homopolymer	8,000	10	157	—	—	—
RT2215A	Low Ethylene Copolymer	1,500	16	143	-22	10	0.87
RT2280A	Low Ethylene Copolymer	8,000	15	146	-22	10	1.09
RT2304A	Medium Ethylene Copolymer	450	30	141	-29	20	—
RT2315A	Medium Ethylene Copolymer	1,500	28	141	-29	20	0.57
RT2330A	Medium Ethylene Copolymer	3,000	25	141	-29	20	0.82
RT2385A	Medium Ethylene Copolymer	8,500	20	141	-29	20	0.79
RT2535A	High Ethylene Copolymer	3,500	45	132	-37	60	0.34
RT2585A	High Ethylene Copolymer	8,500	40	132	-37	60	0.34
RT2715A	Butene-1 Copolymer	1,500	35	110	-23	120	0.38
RT2730A	Butene-1 Copolymer	3,000	30	110	-23	120	0.38
RT2780A	Butene-1 Copolymer	8,000	25	110	-23	120	0.38